



TOP
WATERPROOFING

VELAGUM SPECIAL- SLATED VELAGUM SPECIAL

ELASTO-PLASTOMERIC - POLYOLEFYN POLYMERS BITUMINOUS MEMBRANE BPP

Technical data sheet

REINFORCEMENT	REINFORCED NON WOVEN POLYESTER FABRIC gr. 180
COMPOUND	BITUMEN – ELASTO-PLASTOMER BPP
FINISHING	VELAGUM SPECIAL: SAND; SLATED VELAGUM SPECIAL: NATURAL SLATE
APPLICATION METHOD	FLAME WELDING
<u>DESTINATION OF USE</u>	
SLATED VELAGUM SPECIAL	EN 13707 WATERPROOFING SYSTEM MULTILAYER OR MONOLAYER : FINISHING LAYER EN 13859-1 WATERPROOFING SYSTEM: UNDER TILE
VELAGUM SPECIAL FPC CODE	EN 13707 WATERPROOFING SYSTEM MULTILAYER: FINISHING LAYER - UNDER LAYER GB14/92057



Description

Monoreinforced elasto-plastomeric waterproofing membrane made up of a compound of excellent quality based on distilled bitumen modified with APAO polyolefin polymers reinforced with high grammage continuous thread non woven polyester fabric. It can be supplied either polished or self-protected with natural slate flakes.

Fields of application

Due to its high flexibility, it is suitable for waterproofing structures subjected to mechanical stress, ensuring perfect adhesion to the laying surface. Suitable for waterproofing flat or vaulted civil and industrial coverings, metal or prefabricated structures, vertical retaining walls and foundations.

Stratigraphy

1. Polypropylene film
2. Compound BPP - polyolefyn polymer
3. Non woven polyester fabric reinforcement gr. 180
4. Compound BPP - polyolefyn polymer
5. Finishing:
 - A. VELAGUM SPECIAL: SAND
 - B. SLATED VELAGUM SPECIAL: NATURAL SLATE





TOP
WATERPROOFING

VELAGUM SPECIAL-

SLATED VELAGUM SPECIAL

ELASTO-PLASTOMERIC - POLYOLEFYN POLYMERS BITUMINOUS MEMBRANE BPP

Technical data sheet

Technical Features

Parameter	VELAGUM SPECIAL	SLATED VELAGUM SPECIAL	Unit of measure	Tolerance	Regulations
VISIBLE DEFECTS	Exceeds	Exceeds	Visual	-	EN 1850-1
LENGTH	10	10	m	-1 %	EN 1848-1
WIDTH	1	1	m	-1 %	EN 1848-1
STRAINGHTNESS	Exceeds < 20mm/10m	Exceeds < 20mm/10m	-	-	EN 1848-1
MASS PER UNIT AREA	NPD	4,5	Kg/m ²	- 5 %	EN 1849-1
THICKNESS	4	NPD	mm	- 0,2	EN 1849-1
WATERTIGHTNESS	Exceeds > 60	Exceeds > 60	kPa	-	EN 1928:2000
WATERTIGHTNESS AFTER STRETCHING	NPD	NPD	%	-	EN 13897
EXTERNAL FIRE PERFORMANCE	F ROOF	F ROOF	-	-	EN 13501-5
REACTION TO FIRE	E	E	Classe	-	EN 13501-1
TENSILE PROPERTIES					
MAXIMUM LOAD AT BREAK					
Longitudinal	700	700	N/50 mm	- 20 %	EN 12311-1
Transversal	600	600		- 20 %	
ELONGATION AT BREAK					
Longitudinal	40	40	%	- 15 in ass.	EN 12311-1
Transversal	40	40		- 15 in ass.	
RESISTANCE TO TEARING (nail method)					
Longitudinal	180	180	N	- 30 %	EN 12310-1
Transversal	180	180		- 30 %	
RESISTANCE TO DYNAMIC LOADING	1000	1000	mm	≥	EN 12691
RESISTANCE TO STATING LOADING	15	15	Kg	≥	EN 12730-1
COLD FLEXIBILITY	-20	-20	°C	≤	EN 1109
FLOW RESISTANCE AT ELEVATED TEMPERATURE	140	140	°C	≥	EN 1110
DIMENSIONAL STABILITY	0,3	0,3	%	≤	EN 1107-1
FORM STABILITY UNDER CYCLIC TEMPERAURE CHANGE	NPD	NPD	mm	-	EN 1108
ARTIFICIAL AGEING BEHAVIOUR (FLOW RESISTANCE)	NPD	NPD	ΔT °C	-	EN 1296
ARTIFICIAL AGEING BEHAVIOUR (VISIBLE DEFECTS)	Exceeds	Exceeds	-	-	EN 1297
ADHESION OF GRANULES	-	< 30	%	- 5 in ass.	EN 12039
WATER VAPOUR PROPERTIES	20000	20000	μ	-	EN 1931
RESISTANCE TO ROOTS	NPD	NPD	-	-	EN 13948
PEEL RESISTANCE	NPD	NPD	N/50 mm	-	EN 12316-1
SHEAR RESISTANCE	NPD	NPD	N/50 mm	-	EN 12317-1

Note: NPD = No Performance Declared according to the EU Directive on Construction Products

It is impossible to ensure uniformity of color of slated products, because the only slate manufacturer makes no warranty about. All self-protected products with slate chippings undergo color changes over time as a function of exposure to atmospheric agents. These color variations tend to conform gradually.
AVAILABLE COLOURS OF SLATE: Natural Gray (Standard), Red, Green, White



TOP
WATERPROOFING

VELAGUM SPECIAL-

SLATED VELAGUM SPECIAL

ELASTO-PLASTOMERIC - POLYOLEFYN POLYMERS BITUMINOUS MEMBRANE BPP

Technical data sheet

Packaging

PRODUCT	THICKNESS (mm)	WEIGHT (Kg/m ²)	ROLL DIMENSIONS (m)
VELAGUM SPECIAL	4	-	1x10
SLATED VELAGUM SPECIAL	-	4,5	1x10

Rolls packed on wooden pallets, wrapped with polyethylene heat-shrinkable caps.

Warnings

Store vertically, protecting them from atmospheric agents and from too high or too rigid temperatures. Avoid overlapping rolls and pallets. The contact with solvents and organic fluids can damage the product.

The application surface should be smooth, dry and clean.

The application surface must be previously treated with a suitable bituminous primer, VELQUA, VELABASE or VELAFONDO GRIPERM to eliminate dust and enhance the adhesion of the membrane. The application surface must not have depressions, to avoid stagnation of rain water and must have a sufficient slope to ensure the smooth flow of precipitation (min 1.5%). In the case of applications in vertical development exceeding 2 m or media in strong slope surfaces apply suitable mechanical fasteners in the head of the cloth, then sealed with the junction of the head.

Apply the product at temperature higher than +5°C.

The installation should be discontinued in case of adverse weather conditions (high humidity, rain, etc.).

In order to increase the performance and durability of the coat it is strongly recommended, in the case of non self-protected membranes with slate protection with acrylic paint or aluminous VELACOLOR, VELUMIN, or painting ultra-reflecting REFLEX +. In this case, it is appropriate to wait, for the application, the uniform oxidation of the surface layer of the membrane (3-6 months depending on the exposure and the climatic period and in any case have to verify the oxidation).

The above-mentioned values can be subject to update or change. IIVELA S.r.l. reserves the right to modify them at any time without prior notice. For a correct use of our products, see technical specifications. For further information or any special use, please contact our technical department. Any suggestions or technical information provided represent our best knowledge regarding product characteristics and use. Considering different applications and any possible interference of elements beyond our control, the buyer must declare under his own responsibility that the product is suitable for the intended use.